

DuPont™ Plantex® Cocomat

Technische data/ Technical data/ Technische Daten

Samenstelling Composition Zusammensetzung	100% polypropyleen & lange kokosvezels 100% polypropylene & untreated coconut fibres 100% Polypropylen & Kokoslangfasern	
Kwaliteitskenmerken Quality characteristic Qualitätsmerkmal	Technische data Technical data Technische Daten	Testmethode Test method Prüfmethode
Gewicht Weight Gewicht	540 g/m ²	EN ISO 9864
Dikte Thickness Dicke	6,0 mm	EN ISO 9863-1
Waterdoorlatendheid VIH50 Water permeability VIH50 Wasserdurchlässigkeit VIH50	100 mm/s*	EN ISO 11058
Luchtdoorlatendheid Air permeability Luftdurchlässigkeit	96 m ³ /m ² /min	ASTM D737
Treksterkte Tensile Strength Zugfestigkeit	5,0 kN/m	EN ISO 10319
Breukrek Elongation at break Höchstzugkraftdehnung	40%	EN ISO 10319
Scheurweerstand Tear resistance Reißfestigkeit	220 N	ASTM D4533

* Waarde gebaseerd op 90 g/m² vlies.

* This value refers to the supporting nonwovens layer of 90g/m²

* Wert bezieht sich auf 90 g/m² Vlies.

- Pesticiden, herbiciden of andere land- of tuinbouwproducten kunnen een invloed hebben op de levensduur van het product.
- Pesticides, herbicides or other agricultural products can have an influence on the life span of the product.
- Pestizide, Herbizide oder andere landwirtschaftliche oder gartenbauliche Produkte können die Lebensdauer des Produktes beeinflussen.

Further product information is available upon request. This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own testing. It is not intended, however, to substitute for any testing you can need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions KING RootBarrier makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a licence to operate under or a recommendation to infringe any patent right.