

## DuPont™ Plantex® Cocomat

### Technische data/ Technical data/ Technische Daten

<b>Samenstelling</b> <b>Composition</b> <b>Zusammensetzung</b>	100% polypropyleen & lange kokosvezels 100% polypropylene & untreated coconut fibres 100% Polypropylen & Kokoslangfasern	
<b>Kwaliteitskenmerken</b> <b>Quality characteristic</b> <b>Qualitätsmerkmal</b>	<b>Technische data</b> <b>Technical data</b> <b>Technische Daten</b>	<b>Testmethode</b> <b>Test method</b> <b>Prüfmethode</b>
<b>Gewicht</b> <b>Weight</b> <b>Gewicht</b>	540 g/m <sup>2</sup>	EN ISO 9864
<b>Dikte</b> <b>Thickness</b> <b>Dicke</b>	6,0 mm	EN ISO 9863-1
<b>Waterdoorlatendheid VIH50</b> <b>Water permeability VIH50</b> <b>Wasserdurchlässigkeit VIH50</b>	100 mm/s*	EN ISO 11058
<b>Luchtdoorlatendheid</b> <b>Air permeability</b> <b>Luftdurchlässigkeit</b>	96 m <sup>3</sup> /m <sup>2</sup> /min	ASTM D737
<b>Treksterkte</b> <b>Tensile Strength</b> <b>Zugfestigkeit</b>	5,0 kN/m	EN ISO 10319
<b>Breukrek</b> <b>Elongation at break</b> <b>Höchstzugkraftdehnung</b>	40%	EN ISO 10319
<b>Scheurweerstand</b> <b>Tear resistance</b> <b>Reißfestigkeit</b>	220 N	ASTM D4533

\* Waarde gebaseerd op 90 g/m<sup>2</sup> vlies.

\* This value refers to the supporting nonwovens layer of 90g/m<sup>2</sup>

\* Wert bezieht sich auf 90 g/m<sup>2</sup> Vlies.

- Pesticiden, herbiciden of andere land- of tuinbouwproducten kunnen een invloed hebben op de levensduur van het product.
- Pesticides, herbicides or other agricultural or horticultural products can have an influence on the life span of the product.
- Pestizide, Herbizide oder andere landwirtschaftliche oder gartenbauliche Produkte können die Lebensdauer des Produktes beeinflussen.

Further product information is available upon request. This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own testing. It is not intended, however, to substitute for any testing you can need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions KING RootBarrier makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a licence to operate under or a recommendation to infringe any patent right.